



US009636667B2

(12) **United States Patent**  
**Feyen et al.**

(10) **Patent No.:** **US 9,636,667 B2**  
(45) **Date of Patent:** **May 2, 2017**

(54) **CHA-TYPE ZEOLITE MATERIALS AND METHODS FOR THEIR PREPARATION USING CYCLOALKYAMMONIUM COMPOUNDS**

(71) Applicant: **BASF SE**, Ludwigshafen (DE)

(72) Inventors: **Mathias Feyen**, Hirschberg (DE); **Ulrich Müller**, Neustadt (DE); **Roger Ruetz**, Mannheim (DE); **Thomas Bein**, München (DE); **Karin Möller**, Gräfelfing (DE)

(73) Assignee: **BASF SE**, Ludwigshafen (DE)

(\*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 734 days.

(21) Appl. No.: **13/908,666**

(22) Filed: **Jun. 3, 2013**

(65) **Prior Publication Data**

US 2013/0323164 A1 Dec. 5, 2013

**Related U.S. Application Data**

(60) Provisional application No. 61/654,989, filed on Jun. 4, 2012.

(51) **Int. Cl.**  
**C01B 39/04** (2006.01)  
**B01J 29/70** (2006.01)  
(Continued)

(52) **U.S. Cl.**  
CPC ..... **B01J 29/7015** (2013.01); **B01D 53/565** (2013.01); **B01D 53/9418** (2013.01);  
(Continued)

(58) **Field of Classification Search**  
CPC ..... C01B 39/04; C01B 39/48; B01J 29/7015; B01J 29/86; B01J 29/87; B01J 29/89;  
(Continued)

(56) **References Cited**

**U.S. PATENT DOCUMENTS**

4,544,538 A † 10/1985 Zones

4,610,854 A 9/1986 Zones

(Continued)

**FOREIGN PATENT DOCUMENTS**

CN 1646427 7/2005

CN 101489674 7/2009

(Continued)

**OTHER PUBLICATIONS**

PCT International Search Report and Written Opinion in PCT/IB2013/054569, mailed Nov. 7, 2013, 11 pgs.

(Continued)

*Primary Examiner* — David M Brunzman

(74) *Attorney, Agent, or Firm* — Oblon, McClelland, Maier & Neustadt, L.L.P.

(57) **ABSTRACT**

Aspects of the present invention relate to a process for the preparation of a zeolitic material having a CHA-type framework structure comprising  $\text{YO}_2$  and  $\text{X}_2\text{O}_3$ , wherein said process comprises the steps of:

(1) providing a mixture comprising one or more sources for  $\text{YO}_2$ , one or more sources for  $\text{X}_2\text{O}_3$ , and one or more tetraalkylammonium cation  $\text{R}^1\text{R}^2\text{R}^3\text{R}^4\text{N}^+$ -containing compounds as structure directing agent;

(2) crystallizing the mixture obtained in step (1) for obtaining a zeolitic material having a CHA-type framework structure;

wherein Y is a tetravalent element and X is a trivalent element, wherein  $\text{R}^1$ ,  $\text{R}^2$ , and  $\text{R}^3$  independently from one another stand for alkyl,

wherein  $\text{R}^4$  stands for cycloalkyl, and

wherein the mixture provided in step (1) does not contain any substantial amount of a source for  $\text{Z}_2\text{O}_3$ , wherein Z is P,

(Continued)

